



# Pyramid<sup>®</sup> KD2152 PEEK

## PEEK with 30% Glass Fiber

General	ASTM #	US Value	SI Unit
Form		Pellets (tan)	
Composition (Polyetheretherketone)		PEEK	
Filler Content (Nominal value)	---	30 % Glass Fiber	
Density, lb/in <sup>3</sup>	D792	0.055	1.53 g/ml
Linear Mold Shrinkage, in/in	---	0.008	0.008 cm/cm
Moisture Absorption @24hr., %	D570	0.1	
<b>Mechanical</b>			
Tensile Strength (Break), Kpsi	D638	18	120 MPa
Tensile Modulus, Mpsi	D638	1.17	8.1 GPa
Elongation (Break),%	D638	3.1 %	
Flexural Strength (Yield) Kpsi	D790	28	192 MPa
Flexural Modulus, Mpsi	D790	1.19	8.2 GPa
Izod, Notched, ft-lb/in @1/8"	D256	1.0	0.7 J/cm
Hardness, Rockwell M, Shore D	D2240/D792	M101	D90

This information and all further technical advice are based Polymics' present knowledge and experience. However, neither Polymics Ltd nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this information or its use. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The use of this product resides on the determination of the customer not Polymics Ltd. The customer must determine suitability of any information or material for any contemplated use, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes. Polymics reserves the right to make additions, deletions, or modifications to the information at any time without prior notification

*Polymics • 2215 High Tech Rd. • State College • PA 16803 USA • TEL: (814) 357-5860*

*1006 Guangfu Rd. • Bade City • Taoyuan 33455 Taiwan • TEL: 886 (3) 339-8000*