



Pyramid CC100 PEEK

PEEK with 60% Chopped Carbon Fabric/Tape

General	ASTM #	US Value	SI Unit
Form	--	Compression Molded Shape	
Composition (base resin)	--	PEEK	
Reinforcement	--	Chopped Carbon Fiber/Tape	
Filler Content, Wt%	--	60% nominal	
Color	--	Gray/black	
Density, lb/in ³	D792	0.054	1.5 g/cm ³
Moisture Absorption @24hr., %	D570	0.05	
Mechanical			
Tensile Strength (Break), Kpsi	D638	45	310 MPa
Tensile Modulus, Mpsi	D638	5.2	36 GPa
Elongation (Break),%	D638	1 %	
Flexural Strength (Yield) Kpsi	D790	48	330 MPa
Flexural Modulus Mpsi	D790	4.9	34 GPa
Compressive strength , Kpsi	D695	40	275 MPa
Compressive modulus , Mpsi	D695	3.6	25 GPa
Hardness, Rockwell M	D2240	M110	Shore D96
Izod, Notched, ft-lb/in @ 1/8"	D256	2.1	1.1 J/cm
Thermal			
Melting Point, °F	DSC	644	340°C
Tg (Glass Transition), °F	DSC	289	143°C
Flammability Rating (UL 94)	UL94	V-0	V-0
HDT @ 264 psi	D648	>580	>300°C
Electrical			
Volume Resistivity, Ohm-cm	D257	<100	<100
Surface Resistivity, Ohm-sq	D257	<100	<100



Polymics, Ltd.

High Performance Polymers & Compounds

2215 High Tech Road • State College • PA 16803 • USA

TEL: 1 (814) 357-5860 • FAX: 1 (814) 357-5863

This information and all further technical advice are based Polymics' present knowledge and experience. However, neither Polymics Ltd nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this information or its use. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The use of this product resides on the determination of the customer not Polymics Ltd. The customer must determine suitability of any information or material for any contemplated use, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes. Polymics reserves the right to make additions, deletions, or modifications to the information at any time without prior notification

*Polymics • 2215 High Tech Rd. • State College • PA 16803 USA • TEL: (814) 357-5860
1006 Guangfu Rd. • Bade City • Taoyuan 33455 Taiwan • TEL: 886 (3) 339-8000*

revised 7/25/2010