



Pyramid™ KD2000-J01

Polyetheretherketone, Unfilled, Standard Flow

General	ASTM No.	US Value	SI Unit
Form	---	Pellets (Tan)	
Composition	---	Neat Resin	
Specific Gravity	D792	1.3	
Crystallinity, % maximum	---	30	
Linear Mold Shrinkage, in/in	D955	0.012	
Water Absorption (24hr. @ 23 °C, %)	D570	<0.2	
Melt Flow Index, g/10 min	D1238	20 nominal	
<u>Mechanical</u>			
Tensile Strength (Break), Kpsi	D638	14	97 Mpa
Tensile Modulus, Kpsi	D638	510	3.5 Gpa
Elongation (Break), %	D638	>40	
Flexural Strength (yield), Kpsi	D790	23	159 Mpa
Flexural Modulus Kpsi	D790	510	3.5 Gpa
Izod, Notched, ft-lb/in @ 1/8"	D256	1.8	0.96 J/cm
Izod, Unnotched	D256	No break	
Compressive Strength, Kpsi	D695	19	131 Mpa
Hardness, Rockwell M	D785	M102	Shore D88
<u>Thermal</u>			
Melting Point, °F	DSC/D3418	642	339 °C
Tg °F	DSC/D3418	289	143 °C
Flammability Rating (UL 94)	UL 94	V-0	V-0
HDT@ 264 psi, °F	DMA/D648	320	160 °C
Thermal Conductivity, BTU-In/Hr-ft²-°F	F443/C177	1.73	0.25 W/m-K
CLTE, linear µin/in - °F (<Tg)	D696/E831	26	47 µm/m-°C



Electrical			
Dielectric Strength, V/mil	D149	480	18 KV/mm
Dielectric Constant @ 1 KHz	D150	3.3	
Dissipation Factor @ 1 KHz	D150	0.004	
Volume Resistivity, Ohm-cm x 10¹⁶	D257	1	
Surface Resistivity, Ohm-cm x 10¹⁶	D257	2	

This information and all further technical advice are based Polymics' present knowledge and experience. However, neither Polymics Ltd nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this information or its use. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The use of this product resides on the determination of the customer not Polymics Ltd. The customer must determine suitability of any information or material for any contemplated use, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes. Polymics reserves the right to make additions, deletions, or modifications to the information at any time without prior notification

*Polymics • 2215 High Tech Rd. • State College • PA 16803 USA • TEL: (814) 357-5860
1006 Guangfu Rd. • Bade City • Taoyuan 33455 Taiwan • TEL: 886 (3) 339-8000*