

Celazole[®] TF-60V

Glass Fiber Reinforced Melt Processable PBI

Typical Properties

PROPERTIES	ASTM METHOD	ENGLISH VALUE	METRIC VALUE
MECHANICAL			
Tensile Strength	D-638	19 kpsi	130 MPa
Modulus		1490 kpsi	10,300 MPa
Elongation		1.4%	1.4%
Flexural Strength	D-790	30 kpsi	206 MPa
Modulus		1490 kpsi	10,300 MPa
Compressive Strength	D-695	32 kpsi	220 MPa
Modulus		530 kpsi	3600 MPa
ELECTRICAL			
Dielectric Strength	D-149	410 V/mil	16 KV/mm
Volume Resistivity	D-257	1 X 10 ¹⁶ ohm-cm	1 X 10 ¹⁶ ohm-cm
Dissipation Factor			
1 kHz	D-150	0.000	0.000
10 kHz	D-150	0.001	0.001
Dielectric Constant			
1 kHz	D-150	3.9	3.9
10 kHz	D-150	3.9	3.9
Arc Resistance	D-495	180 seconds	180 seconds
THERMAL			
Coefficient of Linear Thermal Expansion			
75-300°F	TMA	9 x 10 ⁻⁶ in/in°F	17 µm/m°C
Heat Capacity @ 158°F	DSC	0.27 Btu/lb°F	1130 J/Kg°C
Heat Deflection Temperature @ 264 psi	D-648	590°F	310°C
Temperature of Initial (5%) Weight Loss In:			
Air	TGA	1125°F	607°C
Nitrogen	TGA	1175°F	635°C
Thermal Conductivity @ 75°F	F-433	2.5 Btu-in/hr•ft ² °F	0.31 kcal/mh°C
OTHER			
Specific Gravity		1.5	1.5
Hardness, Rockwell A	D-785	30	30
Poisson's Ratio		0.34	0.34
Water Absorption			
24 hours @ 73°F	D-570	0.25%	0.25%
@ Equilibrium	D-570	4.6%	4.6%

PBI Performance Products, Inc.
 9800 Southern Pine Blvd Suite D
 Charlotte, NC 28273 USA
 704.554.3378
www.CelazolePBI.com