

Pyramid[™] KD2000 CAM Tube

Polyetheretherketone (PEEK) Tube

General	ASTM No.	US Value	SI Unit
Specific Gravity	D792	1.3	
Water Absorption (24hr. @ 23 °C, %)	D570	0.2%	
<u>Mechanical</u>			
Tensile Strength	D638	15.2 Kpsi	105 MPa
Tensile Modulus	D638	0.5 Mpsi	3.4 GPa
Tensile Elongation (Break), %	D638	>30%	
Flexural Strength	D790	20 Kpsi	137 MPa
Flexural Modulus	D790	0.5 Mpsi	3.4 GPa
<u>Thermal</u>			
Melting Point, °F	DSC	644	340 °C
CLTE, linear µin/in - °F (<tg)< th=""><th>D696</th><th>2.6</th><th>4.7 μm/m-°C</th></tg)<>	D696	2.6	4.7 μm/m-°C
HDT@ 264 psi, °F	DMA	302	150 °C
Flexural Modulus, °F	D3418	289	143 °C
<u>Flammability</u>			
Flammability (1.6 mm)	UL 94	V-0	
Oxygen Index (3.2 mm)	D2863	38%	
<u>Electrical</u>			
Dielectric Strength	D149	530 V/mil	21 kV/mm
Volume Resistivity	D257	1 x 10 ¹⁴ Ohm	
Surface Resistivity	D257	1 x 10 ¹⁴ Ohm	

This information and all further technical advice are based Polymics' present knowledge and experience. However, neither Polymics Ltd nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this information or its use. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The use of this product resides on the determination of the customer not Polymics Ltd. The customer must determine suitability of any information or material for any contemplated use, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes. Polymics reserves the right to make additions, deletions, or modifications to the information at any time without prior notification

Polymics • 2215 High Tech Rd. • State College • PA 16803 USA • TEL: (814) 357-5860 1006 Guangfu Rd. • Bade City • Taoyuan 33455 Taiwan • TEL: 886 (3) 339-8000